


PETG-CF

/Acrylonitrile Butadiene Styrene/



- ✓ High Impact Resistance
- ✓ High Light Transmission
- ✓ Good Toughness
- ✓ Good Fluidity



■ Material Overview

PETG-CF is a PETG-based composite reinforced with carbon fibers. It not only retains the advantages of high strength and impact resistance but also produces less odor and exhibits lower shrinkage. Additionally, it resists warping and cracking during printing, helping you effortlessly create high-precision, high-quality 3D prints.



Filament Diameter	1.75mm/2.85mm/ 3.50mm
Net Weight	1KG \ Inner Box Dimension: 206*71*208mm \ G.W.: 1.35KG
Package	1KG*10PCs \ Outer Carton Dimension: 382*226*433mm \ G.W.: 14KG/CTN

■ Printing Tips

- Best printing temperature ranges from 220°C to 250°C
- Best phototype can be achieved through 50°C drying for 2-4 hours
- Print Temp: 240-250°C 50 -150mm/s
- Platform Temp.: Glue required if not heated, glue unrequired if heated 50-60°C
- Bubble: no bubble
- (220°C,2.16kg) Breaking Elongation: 3%

■ Colors

 Black (Standardized pantone colors are available)

■ Data Table

Physical Properties	Standard Value	Test Method
Density	1.25-1.28g /cm ³	ASTM D792
MFR (220°C, 2.16KG)	11-16g / 10 minutes	ASTM D1238
Water absorption (saturation, 23°C)	0.3%	ASTM D570
Mechanical Properties	Standard Value	Test Method
Tensile strength	≥45 MPa	ASTM D638
Flexural strength	≥45MPa	ASTM D638
Tensile modulus	≥2,100 MPa	ASTM D638
Notch impact strength (IZOD, 23°C)	≥3KJ/m ²	ISO 180
Elongation at break	≥3.0%	ASTM D638
Accuracy	Standard Value	Test Method
Filament diameter	1.75mm/2.85mm/ 3.50mm	Q/WT 001-2014
Roundness deviation	≤0.02mm	Q/WT 001-2014